

**This Page Is Inserted by IFW Operations  
and is not a part of the Official Record**

## **BEST AVAILABLE IMAGES**

**Defective images within this document are accurate representations of the original documents submitted by the applicant.**

**Defects in the images may include (but are not limited to):**

- **BLACK BORDERS**
- **TEXT CUT OFF AT TOP, BOTTOM OR SIDES**
- **FADED TEXT**
- **ILLEGIBLE TEXT**
- **SKEWED/SLANTED IMAGES**
- **COLORED PHOTOS**
- **BLACK OR VERY BLACK AND WHITE DARK PHOTOS**
- **GRAY SCALE DOCUMENTS**

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problem Mailbox.**

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>B41M 5/24, G03C 7/00, 1/00</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 97/44196</b> <b>(43) International Publication Date:</b> 27 November 1997 (27.11.97)
<b>(21) International Application Number:</b> PCT/GB97/01410 <b>(22) International Filing Date:</b> 23 May 1997 (23.05.97) <b>(30) Priority Data:</b> 9610769.3                      23 May 1996 (23.05.96) <b>GB</b> <b>(71) Applicant (for all designated States except US):</b> SLS BIO-PHILE LIMITED [GB/GB]; Units 1 & 2 Heol Rhosyn, Dafen Industrial Estate, Llanelli, Carmarthenshire SA14 8LX (GB). <b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only):</b> CLEMENT, Robert, Marc [GB/GB]; 11 Plas Road, Rhos, Pontardawe, Swansea SA8 3HD (GB). FIRTH, Naylor [GB/GB]; Ty Carreg, Itton, Chepstow, Gwent NP6 6BZ (GB). <b>(74) Agent:</b> AUSTIN, Hedley, William; Urquhart-Dykes & Lord, Alexandra House, 1 Alexandra Road, Swansea SA1 SED (GB).		<b>(81) Designated States:</b> AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
<b>(54) Title:</b> IMAGE PRODUCTION  <b>(57) Abstract</b>  Visible images are produced by directing pulsed or continuous wave laser radiation imagewise towards a substrate having thereon a plurality of continuous layers each having respectively different hues and/or reflection densities, so as to cause an imagewise distribution of discontinuities in the layers by ablation of respective selected portions of the layers, the distribution of discontinuities constituting the visible image. The substrate has layers comprising pigmented or photochromic material.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

WO 97/44196

PCT/GB97/01410

-1-

### Image Production

The present invention relates to the selective removal of coloured layers present on a substrate so as to form an image.

Most image-forming processes rely upon adding a pigmented material in a carefully controlled manner to a substrate, typically paper, to form an image. In the earliest known processes, a pigmented material is applied to a reversed embossed image which when pressed on to a substrate, typically paper, produced a desired recognisable pattern or image.

Subsequently more refined processes have involved the transfer of coloured materials, often in the form of a dot array, to substrates in order to form a coloured image. Typical of such processes are the ink-jet printing process, processes depending on electrostatic charges attracting pigments to a transfer drum, and the well established technique of photolithography.

All these techniques rely upon adding material to the substrate in a carefully controlled manner. This invention, on the contrary, provides a process where coloured layers, such as the primary colours, black and white may be applied to a substrate, typically paper, tinfoil or aluminium in sequential continuous layers, which layers are selectively removed under carefully controlled conditions to expose desired colours in predetermined areas to form a visible image.

Scraper boards have been used in schools and by artists in a method of forming a pattern by removal of coloured layers present on a substrate of different colour, but the mechanical removal of such layers is very crude and incapable of operating at high tolerances.

According to the present invention there is provided a method of production of a desired visible image, in which laser radiation is directed imagewise at a substrate having thereon a plurality of continuous layers each having respectively different

WO 97/44196

PCT/GB97/01410

-2-

hues and/or reflection densities, so as to cause an imagewise distribution of discontinuities in said layers by instantaneous ablation of respective selected portions of said layers, said distribution of discontinuities constituting said desired visible image.

The use of laser radiation in this way permits selective ablation of material from said layers in a predetermined pattern, at very high tolerances, the radiation being successively focused over a very small diameter to ablate successive shallow discontinuities (pits) in the layers on the substrate. If the depth of such pits is of the order of magnitude of the thickness of an adjacent layer, then the next coloured layer will be revealed. By tuning and/or programming the nature and energy of the laser radiation, it is possible to selectively reveal different layers, so as to generate a black and white or coloured image based upon the way in which the laser source is programmed.

The control of the energy supplied to each point on the respective layers may be achieved by irradiation with a series of rapid pulses of laser radiation, whose amplitude and/or duration determines the total energy emitted. Such pulses of radiation (sometimes referred herein to the "writing laser") may each have a duration of from 1 microsecond to 1 millisecond, typically with a wavelength 600 to 1500 nanometres.

Alternatively, continuous operation of the laser may be used in some embodiments to provide a constant output or constant average output of radiation energy, with imagewise control of the energy being achieved by varying the dwell time (which is the duration of time that the laser radiation impinges a predetermined portion of a layer). This imagewise control may be achieved by using a velocity modulated scan.

In a preferred method according to the invention, the image to be produced is divided into pixels and the hue and/or reflection density at each pixel predetermined by selection of the amplitude, duration or frequency of successive pulses of laser radiation. Each pixel corresponds to a desired pit or discontinuity.

WO 97/44196

PCT/GB97/01410

-3-

In one embodiment, the substrate has thereon two or more pigmented continuous layers each having different hues or reflection densities. The energy absorption characteristics and composition of each layer are generally such that the amount of energy to form a pit by selective removal of a predetermined area element of the layer by ablation is constant across the layer.

In this embodiment, the lowest energy pulse of the writing laser will remove by ablation an element of the first pigmented layer so as to form a discontinuity or pit. If the energy is increased an element of the next layer is removed. Further increases in energy of the writing laser pulses will remove elements of any subsequent layers until finally the support is revealed.

In an alternative embodiment, the substrate has thereon one or more continuous layers each containing photochromic material dispersed therein (possibly in micro-encapsulated form). Each photochromic material changes hue or reflection density on receipt of a predetermined energy dose. The energy absorption characteristics and composition of each layer are such that the amount of energy to achieve a change of hue or reflection density through photochromic action in any given area element of the layer is constant. In the case of encapsulated photochromic dyes, a single layer having a mixture of capsules may be used, such capsules being activated in accordance with the energy and wavelength of the writing laser radiation.

The substrate may be paper, a synthetic polymer film or other material. Preferably the substrate either inherently has a high reflection density or carries a surface coating having a high reflection density. A high reflection density ensures, not only that the image formed has good highlights and contrast, but also that any radiant energy passing through the layers is reflected back to increase the absorption of energy and efficiency of the image production process.

Each layer may be coated uniformly and in a continuous manner on the substrate by conventional coating techniques such as silk screen coating, micro gravure coating, kiss coating, hopper coating and vacuum deposition.

WO 97/44196

PCT/GB97/01410

-4-

Methods of scanning surfaces with laser beams are well known using mirrors, Faraday effect elements, and similar radiation diversion means. The writing laser may be a continuously operating laser, such as a gas laser, a liquid laser or a semiconductor laser. Carbon dioxide lasers and YAG lasers are particularly useful. Tunable lasers may be used to selectively direct energy into appropriately absorbent layers.

Raster scanning of the substrate may be achieved by two dimensional movement of a laser beam across a stationary sheet, or by a line scan while moving the substrate. While the image is being formed by ablation, the irradiated surface may be blown to eliminate ablated particles and prevent settlement on the surface.

The thickness of the various layers on the substrate will influence the amount of energy which is required to ablate material and produce the required image. The thinness of the coat will be limited by the accuracy of the laser beam in penetrating to a specific depth to expose the required pigment. The use of photochemical, as opposed to photothermal, techniques would reduce the power required to produce the surface pattern. In one aspect of the invention, therefore, photochromic pigments are present on the substrate such that their appearance can be changed by exposure to visible laser light.

If the thickness of successive layers on the substrate is of the same order of magnitude as the diameter of the pit created by the laser radiation then the colour of the bottom of the pit cannot be seen at angles of view less than  $45^\circ$  to the surface. Tilting of the surface would therefore produce an extinction of the pattern produced by an array of laser etched pits and the principle could provide a system for securing evaluation of a product produced from the multi-layered coated substrate.

WO 97/44196

PCT/GB97/01410

-5-

A specific embodiment of the invention is now described with reference to the following drawing.

Figure 1 shows an exemplary method according to the invention, in which a laser radiation source 1 directs laser radiation toward a first layer 2 of the substrate and thereby ablates a pit or discontinuity 4 in the layer 3. The depth of the pit or discontinuity 4 is of the order of magnitude of the layer, so as to reveal the coloured layer below. The pit or discontinuity may be of a size corresponding to one pixel.

Depending on the power of the laser radiation, the pit may be formed in one layer (as shown), two layers or more. The laser beam is caused to scan (by means not shown) over the surface of the substrate in a predetermined manner such that the resulting image depends on the zones ablated, and the respective depths of the pits at each point.



WO 97/44196

PCT/GB97/01410

-6-

**Claims:**

1. A method of production of a visible image, in which laser radiation is directed imagewise at a substrate having thereon a plurality of continuous layers each having respectively different hues and/or reflection densities, so as to cause an imagewise distribution of discontinuities in said layers by substantially instantaneous ablation of respective selected portions of said layers, said distribution of discontinuities constituting said desired visible image.
2. A method according to claim 1, wherein said portions of said layers are ablated in a predetermined pattern.
3. A method according to claim 1 or 2, wherein said laser radiation is focused so as to ablate a series of said discontinuities in the form of pits in successive layers.
4. A method according to any of claims 1 to 3, wherein said laser radiation is pulsed, each pulse having a duration of  $1\mu\text{s}$  to  $1\text{ms}$  and having a wavelength in the range of  $600\text{nm}$  to  $1500\text{nm}$ .
5. A method according to any of claims 1 to 3, wherein said laser radiation is continuous wave.
6. A method according to claim 5, wherein a velocity modulated scan controls the energy of said laser radiation.
7. A method according to any of claims 1 to 6, wherein said laser radiation is provided by a tunable laser source programmed to selectively ablate different ones of said layers.

WO 97/44196

PCT/GB97/01410

-7-

8. A method according to any of claims 1 to 7, wherein said image is divided into pixels, the hue and/or reflection density at each pixel being predetermined by selection of the amplitude, duration or frequency of successive pulses of laser radiation.
9. A method according to any of claims 1 to 8, wherein each of said layers comprises a pigmented layer.
10. A method according to claim 9, wherein each successive rise in energy produces a respective discontinuity in each successive one of said layers.
11. A method according to any of claims 1 to 8, wherein each of said layers contains photochromic material.
12. A method according to claim 11, wherein said photochromic material is in encapsulated form, in which at least one said layer comprises a mixture of capsules.
13. A method according to any of claims 1 to 12, wherein substantially the same energy of said laser radiation is applied to each said layer.
14. A method according to any preceding claim, wherein said substrate has a reflective surface.

WO 97/44196

PCT/GB97/01410

1/1




FIG. 1

## INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 97/01410

A. CLASSIFICATION OF SUBJECT MATTER  
 IPC 6 B41M5/24 G03C7/00 G03C1/00

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
 IPC 6 B41M G03C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 008, no. 104 (M-296), 16 May 1984 & JP 59 014993 A (NIPPON DENSHI KK), 25 January 1984, see abstract ---	1-10,13
X	PATENT ABSTRACTS OF JAPAN vol. 014, no. 029 (M-922), 19 January 1990 & JP 01 267092 A (MIYACHI ELECTRIC CO), 24 October 1989, see abstract ---	1-10,13
X	US 2 932 590 A (A. LORENZ ) 2 February 1960 see the whole document --- -/--	1

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

## \* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

24 September 1997

Date of mailing of the international search report

06.11.97

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
 NL - 2280 HV Rijswijk  
 Td. (+31-70) 340-2040, Tx. 31 651 epo nl,  
 Fax (+31-70) 340-3016

Authorized officer

Rasschaert, A

## INTERNATIONAL SEARCH REPORT

Inte Application No

PCT/GB 97/01410

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	NL 7 109 577 A (NICILAAS BUYS) 16 January 1973 see the whole document ---	1
X	EP 0 353 121 A (BREGER GUY) 31 January 1990 see the whole document ---	1
X	US 4 968 526 A (TAKII YASUO ET AL) 6 November 1990 see the whole document ---	1
X	WO 84 02400 A (BATTELLE DEVELOPMENT CORP) 21 June 1984 see the whole document ---	1
X	GB 1 236 423 A (CANON K.K.) 23 June 1971 see the whole document ---	11,12
X	PATENT ABSTRACTS OF JAPAN vol. 015, no. 194 (M-1114), 20 May 1991 & JP 03 051195 A (BROTHER IND LTD), 5 March 1991, see abstract ---	11,12
X	PATENT ABSTRACTS OF JAPAN vol. 010, no. 256 (P-493), 2 September 1986 & JP 61 083533 A (TOSHIBA CORP), 28 April 1986, see abstract ---	11,12
X	US 3 701 663 A (KONDO ASAJI ET AL) 31 October 1972 see the whole document ---	14
A	CH 636 805 A (BOSCH GMBH ROBERT) 30 June 1983 see the whole document -----	1

## INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 97/01410

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2932590 A	12-04-60	NONE	
NL 7109577 A	16-01-73	NONE	
EP 0353121 A	31-01-90	FR 2634690 A	02-02-90
		JP 2074388 A	14-03-90
		US 5021112 A	04-06-91
US 4968526 A	06-11-90	JP 2100213 A	12-04-90
WO 8402400 A	21-06-84	US 4494865 A	22-01-85
		CA 1216153 A	06-01-87
		EP 0127678 A	12-12-84
		JP 60500146 T	31-01-85
GB 1236423 A	23-06-71	BE 721563 A	03-03-69
		DE 1622263 A	03-12-70
		DE 1797388 A	23-12-70
		DE 1797588 A	10-01-74
		DE 1797589 A	08-11-73
		DE 1797590 A	08-11-73
		FR 1602526 A	21-12-70
		GB 1183907 A	11-03-70
		GB 1236421 A	23-06-71
		GB 1236422 A	23-06-71
		GB 1236424 A	23-06-71
		US 3825427 A	23-07-74
		US 3909266 A	30-09-75
		US 3563740 A	16-02-71
US 3701663 A	31-10-72	NONE	
CH 636805 A	30-06-83	NONE	